



TECHNICAL DATA SHEET

Baguette 50x50xL, 60x60xL, 50x80xL, 50x130xL, 50x80-r50xL, 60x250xL

Water absorption. Low absorption paste All the rest of the pastes	EN ISO 10545-3	0 – 4.0 % 3.0 – 7.0 %
Modulus of rupture	EN ISO 10545-4	>17 N/mm ²
Frost resistance	EN ISO 10545-12	Fulfilled
Resistance to thermal shock	EN ISO 10545-9	Fulfilled
Impact resistance (by measurement of coefficient of restitution)	EN ISO 10545-5	0.7-0.9
Fire resistance		A1 _n No need for testing (Decision 96/603/EEC modified)
Stain resistance	EN ISO 10545-14	Group 5 (glazed)
Chemical resistance	EN ISO 10545-13	Group GA (glazed)
Linear thermal expansion	EN ISO 10545-8	5.75 * 10 ⁻⁶ K ⁻¹ (±1)
Weight 50x50xL 60x60xL 50x80xL 50x130xL 50x80-r50xL 60x250xL		3.5 kg/m ±0.5 4.0 kg/m ±0.5 5.5 kg/m ±0.5 7.7 kg/m ±0.5 5.5 kg/m ±0.5 15.0 kg/m ±0.5

Tolerances and dimensions		
Width	In extruding direction	±1.0 mm
Height	Opposite to extruding direction	±3.0 mm
Thickness	EN ISO 10545-2	±3.0 mm
Straightness (in extruding direction)	EN ISO 10545-2	±0.3% of the width